




PETG Yellow, 1.75 mm, 1 kg

3DP-PETG1.75-01-Y

VERSATILE & EASY TO USE

- Polyethylene terephthalate (PETG) is an amorphous thermoplastic of the polyester family
- Perfect combination of clarity and strength. The clarity of PETG approaches that of Acrylic and impact resistance is close to Polycarbonate
- Easy to print with a variety of 3D printers



Features

- Very high strength filament
- Impact Resistant PETG is less brittle than acrylic, and is a lower cost alternative to polycarbonate.
- Chemical Resistant offers superior chemical resistance when compared with many other transparent plastics.
- Environmental friendly as it is considered 100% recyclable
- Very low shrinkage makes printing large flat surfaces a breeze
- Easily printed on any acrylic, glass, Kapton and other printing platform

Packaging

Q'ty in crtn, pcs	8
Crtn volume, CUM	0.034
Crtn weight, kgs	11.36
Individual package size LxWxH:	210x210x90 mm
Carton size LxWxH:	430x430x185 mm
Country of origin	CN
Barcode	8716309090810
Customs code	3916909000

Specifications

Material: PETG, 1.75 mm diameter
 Weight: 1 kg/spool (2.2 lbs)
 Density at 240°C: 1.27 g/cm³
 Melt Flow Index at g/10min, 200°C/ 5kg: 20
 Melt Point: 220 260 °C
 Heat-Deflection-Temperature at 0.455 MPa: 60 80 °C
 Yield Strength at 5mm/min: 50 MPa
 Impact Strength: 8.7 KJ/m²
 Ensile Break: 120 %
 Diameter: 1.75 ± 0.05 mm

System requirements

A 3D printer with 1.75 mm extruder of temperature around 240 °C, suitable for PETG filament

Certificates

